TUBING SELECTION GUIDE

Digital Printing







Printing

3D Printing

Chemical Compatibility (For Reference Only)

CHEMICAL COMPANIENTS (FOR Reference Only)																									
Ink Types					Diluents*							Solvents													
	Product	Materials	Pump Tubing/ Transfer Tubing		UV Cure Ink	Solvent Based Ink	IBOA	HDDA	VCAP	VEEA	ACMO	VMOX	Benzene	Toluene	Xylene	Cyclohexane	Alcohols	Ketones	Mineral Oil	Acetate	Durometer, Shore A (ASTM D2240)	Color	Maximum Temperature for Continuous Use, °F (°C)	Flexibility	Relative Working Pressure Rating
TOP PERFORMERS	Tygon* Ink 1000 View the Whitepaper >>	Polyolefin	Transfer Tubing	✓	✓	✓	Fair	Excellent	Good	Excellent	Excellent	Excellent	Fair	Fair	Fair	Fair	Excellent	Good	Fair	Good	90	Black	131 (55)	Better	Best
TOP PER	Tygon* 2375-D2	Polyolefin	Transfer Tubing	✓	✓	✓	Poor	Good	Fair	Fair	Good	Fair	Poor	Poor	Poor	Poor	Excellent	Fair	Poor	Fair	75	Black	130 (54)	Best	Better
	<u>Tygon* 2375</u>	Polyolefin	Transfer Tubing	✓		✓	Poor	Good	Fair	Fair	Good	Fair	Poor	Poor	Poor	Poor	Excellent	Fair	Poor	Fair	75	Clear	130 (54)	Best	Better
	<u>Tygon® 2375-D5</u>	Polyolefin	Transfer Tubing	✓	✓	✓	Poor	Good	Fair	Fair	Good	Fair	Poor	Poor	Poor	Poor	Excellent	Fair	Poor	Fair	75	Blue	130 (54)	Best	Better
	Tygon* LP-1200	Fluoropolymer Lined Polyurethane	Transfer Tubing	✓		✓	Excellent	Fair	Poor	Poor	Poor	Poor	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Excellent	78	Natural	180 (82)	Best	Better
	<u>Versilon™ FEP</u>	Fluoropolymer	Transfer Tubing	✓	✓	✓	Excellent	Excellent	Excellent	Excellent	Excellent	D60	Natural	402 (206)	Better	Best									
	<u>Versilon™ PFA</u>	Fluoropolymer	Transfer Tubing	✓	✓	✓	Excellent	Excellent	Excellent	Excellent	Excellent	D60	Natural	402 (206)	Better	Best									
	Tygon® A-60-G	Thermoplastic Elastomer	Pump Tubing	✓			Poor	Good	Fair	Fair	Good	Fair	Poor	Poor	Fair	Fair	Excellent	Poor	Poor	Excellent	61	Black	275 (135)	Better	Good
	Tygon* XL-60	Thermoplastic Elastomer	Pump Tubing	✓		✓	Poor	Good	Fair	Fair	Good	Fair	Poor	Poor	Fair	Fair	Fair	Poor	Fair	Excellent	60	Clear	250 (121)	Good	Good
	<u>Versilon™ 2001</u>	Polyolefin	Pump Tubing	√		✓	Poor	Fair	Fair	Good	Good	Fair	Poor	Poor	Fair	Fair	Excellent	Fair	Poor	Good	69	Clear	135 (57)	Better	Good





* Based on the results of a 28-day soak at 40°C.

Chemical Ratings: Excellent (≤+/-2% wt.%) Applies to diluents only. Good = (\leq +/-5% wt.% + \geq +/-2%) Fair (≤+/-20% wt.%)

