

Versilon® TLCTCO Hose

SMOOTH BORE FLUOROPOLYMER CONVOLUTED OUTER COVER HOSE

With increased flexibility, easily identified by a reduced force-to-bend and small minimum bend radius, Saint-Gobain's Versilon® TLCTCO hose will quickly demonstrate reasons to include this hose construction in your demanding process applications.

While achieving flexibility in hose assemblies is always a goal in hose design considerations, pressure limitations, long-term service life, hose durability and ease of handling must also be considered. TLCTCO meets these objectives and is ideally suited for many critical process applications in the chemical, pharmaceutical and industrial marketplace.

High purity, ultra smooth FEP fluoropolymer liners used in the manufacture of TLCT series hose have been leading the process industry for many years. The TLCTCO hose series is an improvement in flexibility of a proven, reliable, industry leading product line that will add increased productivity, ease of handling, better value and increased service.

Typical Applications

- Load cells
- Skid transfer
- Pumping stations/portable pumps
- Vessel or tank transfer
- Rail car loading/unloading
- Transfer lines
- Chemical process lines

Features and Benefits

- Reduced force-to-bend
- Improved bend radius
- Ultra-flexible, easy to handle, kink resistant
- Smooth ID when bent
- High pressure rating
- Sterilizable, autoclavable
- Non-aging liner
- Full vacuum rated
- Resistant to chemicals, ozone and abrasion

Regulatory Compliance

- Inner Tube: The FEP inner tube extracts meet the requirements of USP Plastic Class VI. The FEP inner tube material meets the requirements of FDA 21 CFR 177.1550*
- Hose Assembly: 3-A Sanitary Standard 62-02

*Use restrictions and limitations may apply.



Versilon® TLCTCO Hose

Versilon® TLCTCO Hose Specifications

Part Number	Inside Diameter		Outside Diameter		Maximum Working Pressure		Minimum Burst Pressure		Minimum Bend Radius		Vacuum Hg @ 70°F		Weight	
	(in)	(mm)	(in)	(mm)	(psi)	(MPa)	(psi)	(MPa)	(in)	(mm)	(in)	(mm)	(lb/ft)	(kg/m)
3812TLCTCO	3/4	19.1	1.30	33.0	400	2.76	1,600	11.03	2.50	63.5	29.9	760	0.63	0.94
3816TLCTCO	1	25.4	1.56	39.6	350	2.41	1,400	9.65	3.75	95.3	29.9	760	0.79	1.18
3820TLCTCO	1-1/4	31.8	1.78	45.2	320	2.21	1,280	8.83	7.00	177.8	29.9	760	0.93	1.38
3824TLCTCO	1-1/2	38.1	2.13	54.1	300	2.07	1,200	8.27	7.00	177.8	29.9	760	1.16	1.73
3832TLCTCO	2	50.8	2.68	68.1	250	1.72	1,000	6.89	8.75	222.3	29.9	760	1.61	2.40

! Important:

Burst pressure ratings at ambient 70°F (21°C). See applicable notes below on vacuum/pressure ratings at temperatures other than ambient.

Working Pressure is given at 70°F; decrease working pressure 1% for every 2°F above 212°F.

Vacuum Rating is given at 70°F; decrease vacuum rating 1% for every 2°F above 212°F. For 1-1/4" and larger sizes, vacuum rating decreases when installed less than 2X minimum bend radius.

Flare-Thru fittings are pressure rated only. Not rated for vacuum service.

Extended Service Life Tip: Saint-Gobain suggests using full-length anti-kink armor casing or at least 16" to 24" long anti-kink cuffs at each fitting end to help reduce the strain on the crimp collar and fittings in high load installations. Prolonged service at elevated temperatures will reduce total service life.

NOTE: Weights and outside diameter dimensions are nominal. Data given is for hose only. End fitting vs. hose pressure limitations must be considered and the lower of the two ratings must be used on assemblies.

Construction

Inner Tube:	FEP
Cover:	Convuluted EPDM rubber
Reinforcement:	Multiple polyester plycord and EPDM rubber Double helix, high tensile strength carbon steel wire
Color:	Green with a white layline in green lettering
Temperature Rating:	-40°F to +350°F -40°C to +177°C
Maximum Length:	100 feet (all sizes)

Fitting Options

Versilon® Crimp Style Fittings

- Over 40 styles of stocked crimp-style fittings in a wide range of materials
- Standard: 316L stainless steel (wetted surfaces)

Common Media

- Hydrofluoric acid
- Hydrochloric acid
- Sulfuric acid
- Paint

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Saint-Gobain
210 Harmony Road
Mickleton, NJ 08056
USA

www.ics.saint-gobain.com



NOTE: The data and details given in this document are correct and up to date. This document is intended to provide information about the product and possible applications. This document is not the product specification and does not provide specific features, nor does it guarantee product performance in specific applications. Saint-Gobain cannot anticipate or control the conditions of the field and for this reason strongly recommends that practical tests are conducted to ensure that the product meets the requirements of a specific application.

Versilon® is a registered trademark of Saint-Gobain Performance Plastics Corporation.