

Tygon[®] Power LP-1200 Tubing

CLEAR, HIGH-PERFORMANCE FUEL TUBING FOR SMALL ENGINES

Designed to Meet Clean Air Regulatory Standards and Maintain Flexibility in Frigid Temperatures

Tygon[®] Power LP-1200 tubing is low permeation fuel tubing specially designed to meet new EPA and CARB evaporative emission standards of 15g/m²/day. The patent-pending design and robust multi-layer construction offers superior fitting retention and resistance to swelling, hardening and cracking caused by hydrocarbon-based fluids.

Tygon[®] Power LP-1200 tubing is also designed to retain flexibility in frigid temperatures. Its formulation helps to prevent rupture while maintaining tube flexibility, lowering the risk of fuel system failure in cold weather conditions. Available in both standard and custom sizes and colors, Tygon[®] Power LP-1200 tubing is ideal for lawn and garden power equipment, small engine fuel lines, and lubricating oil and grease transfer lines. It meets ANSI B175.1 Annex D standard.

Available Sizes

Tygon[®] Power LP-1200 tubing is available in five standard stock sizes:

- 2/25" (2.032 mm) ID x 7/50" (3.556 mm) OD
- 3/32" (2.381 mm) ID x 3/16" (4.762 mm) OD
- 1/8" (3.175 mm) ID x 1/4" (6.350 mm) OD
- 3/16" (4.762 mm) ID x 5/16" (7.937 mm) OD
- 1/4" (6.350 mm) ID x 3/8" (9.525 mm) OD

Typical Applications

- Brush Cutters
- Chainsaws
- Cut-off Machines
- Earth/Ice Augers
- Edgers
- Engine Drills
- Hedge and Weed Trimmers
- Leaf Blowers
- Pole Pruners
- Split-boom Products
- Tillers



Features and Benefits

- Transparent and easy to diagnose fuel flow or leak problems
- High purity fluoropolymer inner liner and reduces the risk of fuel system fouling from extractable solids found in typical rubber products
- Superior fuel resistance and compatible with ethanol-enhanced fuels and worry-free operation
- Excellent fitting retention and 100% seal for optimum safety
- Superior flexibility and easy assembly, routing and optimized fuel pick-up
- Excellent elasticity and prevents "necking" from over-stretching during installation
- Submersible* and applicable with most fuel applications

*Not recommended for reuse in higher temperature applications.



Tygon® Power LP-1200 Tubing

Tygon® Power LP-1200 Tubing

Part Number	ID		OD		Wall Thickness		Length		Min. Bend Radius		Max. Working Pressure		Vacuum Rating	
	(in.)	(mm)	(in.)	(mm)	(in.)	(mm)	(ft.)	(m)	(in.)	(mm)	73°F (psi)*	23°C (bar)	inHg at 73°F	mmHg at 23°C
ALR00700**	2/25	2.032	7/50	3.556	3/100	0.762	50	15.24	1/4	6.350	70	4.8	29.9	1x10 ⁻⁴
ALR00165	3/32	2.381	3/16	4.762	3/64	1.194	50	15.24	1/4	6.350	65	4.5	29.9	1x10 ⁻⁴
ALR00007	1/8	3.175	1/4	6.350	1/16	1.588	50	15.24	3/8	9.525	60	4.1	29.9	1x10 ⁻⁴
ALR00012	3/16	4.762	5/16	7.937	1/16	1.588	50	15.24	1/2	12.700	45	3.1	29.9	1x10 ⁻⁴
ALR00017	1/4	6.350	3/8	9.525	1/16	1.588	50	15.24	5/8	15.875	30	2.1	29.9	1x10 ⁻⁴

*Working pressures are calculated at a 1:5 ratio relative to burst pressure using ASTM D1599.

** ALR00700 is not 2020 CARB certified.

Typical Physical Properties

Property	ASTM Method	Value or Rating
Durometer Hardness, Shore A, 15s	D2240	78
Tensile Strength, psi (MPa)	D412	3,600 (24.8)
Ultimate Elongation, %	D412	475
Tear Resistance, lb-f/in (kN/m)	D1004	500 (87.5)
Specific Gravity	D792	1.27
Water Absorption, % at 73°F (23°C) for 24 hrs.	D570	0.70
Compression Set Constant Deflection, % at 158°F (70°C) for 22 hrs.	D395 Method B	35
Brittleness Temp., °F (°C)	—	-20 (-28)
Maximum Recommended Operating Temp., °F (°C)	—	180 (82)
Tensile Stress, at 100% Elongation, psi (MPa)	D412	668 (4.6)
Tensile Set, at 75% Elongation	D412	90
Color	—	Translucent
Brittleness by Impact Temp., °F (°C)	D746-98	< -130 (< -90)
Low Temperature Flexibility, °F (°C)	—	-40 (-40)

Unless otherwise noted, all tests were conducted at room temperature 73°F (23°C). Values shown were determined on 0.075" (1.905 mm) thick extruded strip, 0.075" (1.905 mm) thick molded ASTM plaques or molded ASTM durometer buttons.

Product Characteristics

Opacity	Flammability Rating	Fuel Permeation (total tube), g/m ² /d	
Translucent	UL 94 HB	CA Phase II, 40°C	<15
		CE 10, 40°C	<15

Regulatory Compliance

40 CFR 1060 EPA Regulation	Conforms
CA SORE Chapter 15, Article I	Conforms
CA Component Executive Order Number	Q-19-067B
CA Component Executive Order Size Limitations	3/32" ID and above
EPA Certification Number	TSGNPLINE120-001
ANSI B175.1 Annex D Standard	Conforms

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.



Saint-Gobain
2664 Gilchrist Road
Akron, OH 44305
USA

Saint-Gobain
BP 14-La Mothe-aux-Aulnaies
F-89120 Charny, France

Saint-Gobain
1476 Kun Yang Road
Minhang Economic &
Technological Development Zone
Shanghai, China 200245



NOTE: The data and details given in this document are correct and up to date. This document is intended to provide information about the product and possible applications. This document is not the product specification and does not provide specific features, nor does it guarantee product performance in specific applications. Saint-Gobain cannot anticipate or control the conditions of the field and for this reason strongly recommends that practical tests are conducted to ensure that the product meets the requirements of a specific application.

Tygon® is a registered trademark of Saint-Gobain Performance Plastics Corporation.