

# Versilon™ SPX-60 FB

## Silicone Tubing for Food and Beverage Applications

Peroxide-cured Versilon SPX-60 FB silicone tubing is designed for use in food and beverage applications where flexibility, resiliency and durability are required. This tubing formulation optimizes critical physical properties such as tensile strength, elongation and compression set, resulting in a more physical durable product. The smooth inner surface of the tubing reduces the risk of particulate entrapment during the dispensing of beverages such as coffee, tea, soft drinks, and fruit juices.

### Regulatory Compliance

Versilon SPX-60 FB tubing is compliant with\*:

- The applicable requirements of FDA Food Additive Regulations
- Regulation (EC) No 1935/2004 for its intended use
- French Order of 25 November 1992 on silicone materials

\* For complete compliance information and appropriate use instructions, please refer to the detailed document of compliance. The complete compliance information and use instructions can be obtained by contacting Saint-Gobain.



### Features and Benefits

- Provides resiliency, long-life, and durability
- Smooth inner bore reduces risk of particulate entrapment
- Withstands temperature extremes from -50°C to 200°C

### Typical Applications

- Food and Beverage Dispensing
- Cosmetic Dispensing & Production

## Sizes

| Part Number | ID   | Wall Thickness | OD   | Length   |
|-------------|------|----------------|------|----------|
|             | (mm) | (mm)           | (mm) | (meters) |
| ABX6FB001-C | 0.5  | 1.0            | 2.5  | 50       |
| ABX6FB002-C | 1.0  | 1.0            | 3.0  | 50       |
| ABX6FB003-C | 1.5  | 0.75           | 3.0  | 50       |
| ABX6FB004-C | 2.0  | 1.0            | 4.0  | 50       |
| ABX6FB005-C | 2.0  | 1.75           | 5.5  | 50       |
| ABX6FB006-C | 2.0  | 2.0            | 6.0  | 50       |
| ABX6FB007-C | 3.0  | 1.0            | 5.0  | 25       |
| ABX6FB008-C | 3.0  | 1.25           | 5.5  | 25       |
| ABX6FB009-C | 3.0  | 1.5            | 6.0  | 25       |
| ABX6FB010-C | 3.0  | 2.0            | 7.0  | 25       |
| ABX6FB011-C | 4.0  | 1.0            | 6.0  | 25       |
| ABX6FB012-C | 4.0  | 1.5            | 7.0  | 25       |
| ABX6FB013-C | 4.0  | 2.0            | 8.0  | 25       |
| ABX6FB014-C | 4.0  | 3.0            | 10.0 | 25       |
| ABX6FB015-C | 5.0  | 1.0            | 7.0  | 25       |
| ABX6FB016-C | 5.0  | 1.5            | 8.0  | 25       |
| ABX6FB017-C | 5.0  | 2.0            | 9.0  | 25       |
| ABX6FB018-C | 5.0  | 2.5            | 10.0 | 25       |
| ABX6FB019-C | 6.0  | 1.0            | 8.0  | 25       |
| ABX6FB020-C | 6.0  | 1.5            | 9.0  | 25       |
| ABX6FB021-C | 6.0  | 2.0            | 10.0 | 25       |
| ABX6FB022-C | 6.0  | 3.0            | 12.0 | 25       |
| ABX6FB023-C | 7.0  | 1.5            | 10.0 | 25       |
| ABX6FB024-C | 7.0  | 2.0            | 11.0 | 25       |
| ABX6FB025-C | 7.0  | 2.5            | 12.0 | 25       |
| ABX6FB026-C | 7.0  | 3.0            | 13.0 | 25       |
| ABX6FB027-C | 8.0  | 1.5            | 11.0 | 25       |
| ABX6FB028-C | 8.0  | 2.0            | 12.0 | 25       |
| ABX6FB029-C | 8.0  | 3.0            | 14.0 | 25       |
| ABX6FB030-C | 8.0  | 4.0            | 16.0 | 25       |
| ABX6FB031-C | 8.5  | 1.75           | 12.0 | 25       |
| ABX6FB032-C | 9.0  | 2.0            | 13.0 | 25       |
| ABX6FB033-C | 10.0 | 2.0            | 14.0 | 25       |
| ABX6FB034-C | 10.0 | 3.0            | 16.0 | 25       |
| ABX6FB035-C | 10.0 | 4.0            | 18.0 | 25       |
| ABX6FB036-C | 10.0 | 6.5            | 23.0 | 25       |
| ABX6FB037-C | 12.0 | 1.75           | 15.5 | 25       |
| ABX6FB038-C | 12.0 | 2.5            | 17.0 | 25       |
| ABX6FB039-C | 15.0 | 3.0            | 21.0 | 25       |
| ABX6FB040-C | 18.0 | 3.0            | 24.0 | 10       |
| ABX6FB041-C | 20.0 | 3.5            | 27.0 | 10       |
| ABX6FB042-C | 25.0 | 5.0            | 35.0 | 10       |
| ABX6FB043-C | 30.0 | 5.0            | 40.0 | 10       |
| ABX6FB044-C | 40.0 | 5.0            | 50.0 | 10       |
| ABX6FB045-C | 50.0 | 5.0            | 60.0 | 10       |

## Typical Physical Properties

| Property  | ASTM Method | Value or Rating                |
|---|-------------|--------------------------------|
| Durometer Hardness (Shore A)  | D2240-02    | 61 ±4                          |
| Color   | -           | Translucent                    |
| Tear Resistance (N/mm)  | D1004-94    | 22.3                           |
| Specific Gravity  | D792-00     | 1.16                           |
| Compression Set<br>Constant Deflection (%)<br>at 70°C (158°F) for 22 hrs. | D395-01 B   | 26                             |
| Maximum Recommended<br>Operating Temperature °C (°F)                      | —           | -50°(-58°) to 200°C<br>(392°F) |
| Tensile Strength (MPa)  | D412-98     | 11.2                           |
| Ultimate Elongation (%)   | D412-98     | 532                            |

Unless otherwise noted, all tests were conducted at room temperature 72°F (22°C). Values shown were determined on 0.075" (1.905 mm) thick extruded strip or 0.075" (1.905 mm) thick molded ASTM plaques or molded ASTM durometer buttons.



## Saint-Gobain Performance Plastics

5 rue du Dauphiné  
Zone Industrielle de Chesnes  
BP712 Saint-Quentin-Fallavier Cedex,  
France 38297

Tel: (33) 0-4-74-94-82-34

[www.ics.saint-gobain.com](http://www.ics.saint-gobain.com)

**NOTE:** The data and details given in this document are correct and up to date. This document is intended to provide information about the product and possible applications. This document is not the product specification and does not provide specific features, nor does it guarantee product performance in specific applications. Saint-Gobain cannot anticipate or control the conditions of the field and for this reason strongly recommends that practical tests are conducted to ensure that the product meets the requirements of a specific application.

Versilon™ is a trademark of Saint-Gobain Performance Plastics.